



升华集团德清华源颜料有限公司
SHENGHUA GROUP DEQING HUAYUAN
PIGMENT CO., LTD.



TECHNICAL DATA

Edition of: 2010-12-8

Trade name	Iron oxide yellow			
Type	P-586			
REACH	Registration No. 01-2119457554-33-0014			
Chemical name	Iron hydroxide oxide (α -FeOOH)			
Delivery form	Powder			
Colour index	Pigment yellow 42 (77492)			
CAS No./EC No.	51274-00-1/257-098-5			
Specifications	Contents (α -FeOOH)	%	≥ 86	ISO1248
	Oil absorption	ml/100g	25~35	ISO787-5
	Res. on 325 mesh	%	≤ 0.3	ISO787-7
	Water soluble salts	%	≤ 0.3	ISO787-3
	Moisture	%	≤ 1.0	ISO787-2
	pH value		3~7	ISO787-9
	Ignition loss (1,000°C, ½ h)	%	≤ 14	DIN55913
	Bulk density	g/cm ³	0.7~1.0	ISO787-11
	Specific gravity	g/cm ³	4.1	ISO787-10
	Particle size BET	μm	0.1x0.6	Electron Micrographs
	Dispersibility (Hegman)	μm	20/25/30	ISO787-20
	Tinting Strength (Compared with Standard)	%	95~105	ISO787-24
	Color Difference ΔE (Compared with Standard)		≤ 1.0	ISO787-1
Sales packing	In 25kg paper bag/900kg bulk bag then palletized			
Transport & Storage	Protect against weathering / Store in a dry place			
Safety	The product is not classified as hazardous under EC 1907/2006 & EC 1272/2008			

Unit C, 11 Floor, Baima Mansion, Miduqiao Road, Hangzhou, 310005 China

Tel: +86 (571) 85 81 21 60 Fax: +86 (571) 85 81 21 61

E-mail: info@ironoxide.com.cn http://www.ironoxide.com.cn